

REPORT DOCUMENTATION PAGEForm Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. **PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.**

1. REPORT DATE (DD-MM-YYYY) 03-12-2004		2. REPORT TYPE Technical Paper (View Graph)		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Preparation of Benzophenone Modified Poly (dimethylsiloxane) Thermosets				5a. CONTRACT NUMBER F04611-99-C-0025	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Joseph M. Mabry, William P. Weber				5d. PROJECT NUMBER 2303	
				5e. TASK NUMBER M1A3	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) ERC Incorporated 555 Sparkman Drive Huntsville, AL 35816-0000				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory (AFMC) AFRL/PRSB 4 Draco Drive Edwards AFB CA 93524-7160				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S NUMBER(S) AFRL-PR-ED-VG-2004-069	
12. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES American Chemical Society Anaheim, CA, 1 April 2004					
14. ABSTRACT					
20040503 186					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
					Linda Talon
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area code)
Unclassified	Unclassified	Unclassified	A	22	(661) 275-5865



Preparation of Benzophenone Modified Poly(dimethylsiloxane) Thermosets

Joseph M. Mabry¹ and William P. Weber²

¹ERC, Inc., Air Force Research Laboratory
Edwards AFB, CA 93524

² Loker Hydrocarbon Research Inst., Dept. of Chemistry
University of Southern California 90089-1661

Best Available Copy DISTRIBUTION A. Approved for public release; distribution unlimited.



Objective




While the **Ru** catalyzed incorporation of aromatic ketones into siloxane polymer backbones adds various properties to the polymers, the characteristic properties of poly(dimethylsiloxane) (PDMS), such as low glass transition temperature (T_g), are lost.

The **Ru** catalyzed chemical modification of a PDMS copolymer may allow the addition of the properties of the ketones, while retaining the properties of PDMS.




Poly(dimethylsiloxane) (PDMS)



- Water repellant/Hydrolysis resistant
- Thermal and electrical insulator
- Oxidative resistant
- Biocompatible
- Low T_g of approximately -125 °C
- Thermally degrades at approximately 300 °C



Murai Reaction




Murai has shown that $\text{RuH}_2(\text{CO})(\text{PPh}_3)_3$ (**Ru**) catalyzes the addition of vinylsilanes to aromatic ketones in high yield.

Kakiuchi, F.; Sekine, S.; Tanaka, Y.; Kamatani, A.; Sonoda, M.; Chatani, M.; Murai, S. *Bull. Chem. Soc. Jpn.*, **195**, 68, 62.

DISTRIBUTION A. Approved for public release; distribution unlimited.





Catalyst Activation



The catalyst, dihydridocarbonyltris(triphenylphosphine)ruthenium (Ru), prepared from RuCl_3 ,⁴ is activated with a stoichiometric amount of styrene. Hydrogen is lost from the ruthenium center and ethyl benzene is produced. This activates the catalyst by creating a site of coordinate unsaturation.⁵





Catalytic Cycle



(R = phenyl or mesityl)




Chemical Modification



This poster reports the **Ru**-catalyzed addition of benzophenone to **1%** vinylmethyl PDMS.



Addition of 2,4,6-Trimethylbenzophenone





Glass Transition Temperature




Compound	Starting Polymer	Benzophenone	2,4,6-Trimethylbenzophenone
M_w/M_n	33,300/20,700	34,200/19,800	39,300/22,500
T_g	-125 °C	-123 °C	-123 °C

While thermal stability is increased, low T_g s are retained.



Thermal Stability




Both copolymers are stable in nitrogen to 350 °C.

DISTRIBUTION A. Approved for public release; distribution unlimited.




Thermal Stability



Both copolymers are stable in air to 350 °C.



TGA Experiment



Polymer sample is heated in TGA analyzer at 300 °C for one hour.



Molecular Weight Increase




	Benzophenone	2,4,6-Trimethylbenzophenone
Starting M_w/M_n	34,200/19,800	39,300/22,500
M_w/M_n after heating	157,900/75,500	119,100/57,700

- M_w triples or better upon heating at 300 °C for one hour
- Polymer remains soluble
- Structural changes not visible in NMR spectra.



α,ω -Substituted PDMS



Starting Material	100 cSt	200 cSt	1000 cSt	20,000 cSt
Starting M_w/M_n	9,200/5,400	13,000/6,800	29,900/18,200	87,600/44,800
Starting T_g	-125 °C	-124 °C	-125 °C	-125 °C
Product M_w/M_n	10,300/7,000	18,200/13,300	34,300/21,400	96,300/59,700
Product T_g	-125 °C	-123 °C	-124 °C	-125 °C

Low T_g s are also retained in α,ω -substituted polymers.

DISTRIBUTION A. Approved for public release; distribution unlimited.



TGA Experiment




Starting Material	100 cSt	200 cSt	1000 cSt	20,000 cSt
Starting M_w/M_n	10,300/7,000	18,200/13,300	34,300/21,400	96,300/59,700
Product M_w/M_n	12,500/7,800	19,600/13,900	44,900/28,500	127,200/70,200

- M_w increases by up to 32% after heating at 300 °C
- Polymer remains soluble
- Structural changes not visible in NMR spectra.



The Elbs Reaction




Pyrolysis of 2-methylbenzophenone results in the formation of anthracene and fluorene.

Gu, T. Y.; Weber, W. P. *J. Org. Chem.* **1980**, *45*, 2541.
DISTRIBUTION A. Approved for public release; distribution unlimited.





Pyrocondensation of Anthracene



Pyrolysis of anthracene results in the formation of bianthracenyls.



Model Compound




Higher Molecular Weight Products

- Model compound was prepared and pyrolyzed
- Conversion to anthracene was confirmed by UV
- Higher molecular weight products were observed

DISTRIBUTION A. Approved for public release; distribution unlimited.



Polymer Crosslinking



- Crosslinks may interfere with reversion reaction




Summary



- Low T_g s are retained with the addition of benzophenones
- Thermal stability is increased in both nitrogen and air
- Molecular weight increases upon heating to 300 °C
- Conversion to anthracene was confirmed by UV
- Pyrocondensation of anthracene may form cross links
- Cross links may interfere with reversion reaction



Notes



- Typical characteristics of PDMS (low T_g and thermal stability) were successfully retained.
- Characteristics of aromatic diketones (electrochemical and photochemical) were successfully added.
- Poly(dimethylsiloxane) containing 0.8% vinylmethyl units was purchased from Gelest.
- Virtually all vinyl groups were substituted with aromatic units when analyzed by NMR.



Acknowledgement



We would like to thank the National
Science Foundation for their support.

DISTRIBUTION A. Approved for public release; distribution unlimited.



References



- (1) Kakiuchi, F.; Sekine, S.; Tanaka, Y.; Kamatani, A.; Sonoda, M.; Chatani, M.; Murai, S. *Bull. Chem. Soc. Jpn.*, **195**, 68, 62.
- (2) Sargent, J. R.; Weber, W. P. *Polymer* **1999**, 40, 3795.
- (3) Guo, H.; Tapsak, M. A.; Weber, W. P. *Polym. Bull.* **1994**, 33, 417.
- (4) Levison, J. J.; Robinson, S. D., *J. Chem. Soc., A* **1970**, 2947.
- (5) Guo, H.; Wang, G.; Tapsak, M. A.; Weber, W. P. *Macromolecules* **1995**, 28, 5686.
- (6) Thornberry, M. P.; Slobodnick, C.; Deck, P. A. *Organometallics* **2000**, 19, 5352.
- (7) Toma, S.; Solcaniova, E.; Nagy, A. G. *J. Organomet. Chem.* **1985**, 288, 331.
- (8) Asahara, M.; Natsume, S.; Kurihara, H.; Yamaguchi, T.; Erabi, T.; Wada, M. *J. Organomet. Chem.* **2000**, 601, 246.

Best Available Copy

DISTRIBUTION A. Approved for public release; distribution unlimited.